



Spectrum Cutting Solutions Pvt Ltd

## Product Data Sheet

### “SP-SSPW”

#### Product Description:

“SP -SSPW” is Rust Preventive Additive Package specially designed with blend of film forming material, corrosion inhibitor, and selected Waxes to enhance the performance in Salt spray & Humidity Atmosphere.

#### Typical Properties:

- |                         |                     |
|-------------------------|---------------------|
| 1) Color                | : Light Brown       |
| 2) Appearance           | : paste .           |
| 3) Acid value           | : Max 20. Mg KOH/gm |
| 4) 10%solubility in MTO | : Bright & clear    |
| 5) Drop point           | : 35-45 Deg         |

#### Key performance:

1. Excellent Corrosion protection.
2. Excellent Dewatering properties.
3. Cost Effective
4. Good protection in Salt Spray & Humidity Atmosphere

#### Guideline Formulations:

Raw material	RPO 1	RPO 2	RPO3
SP-SSPW(HEAT AT 80DEG)	15	13	5
SN 500 GR 1	10	12	20
MTO	75	75	75
BUTYL CELLOSOLVE	1.0	1.0	1.0
Total	100	100	100

#### Result of RPO

Properties	Result RPO 1	Result RPO 2	Result RPO 3
Salt Spray Test(ASTM B-117)	72 hrs	48hrs	24hrs
Dewatering	Passes	Passes	Passes
De-Emulsification	Passes	Passes	Passes
Humidity (ASTM D1748)	60days	45 day	25day

Flamingo, Empire, ‘A’ Wing, Flat No 502, Survey No. 22, Behind Maratha Mandir  
Near Pristine Fontana Bldg., Bavdhan (Khurd), Pune -411021, Maharashtra

[info@spectrumcspl.com](mailto:info@spectrumcspl.com) [www.spectrumcspl.com](http://www.spectrumcspl.com)



## Spectrum Cutting Solutions Pvt Ltd

### **Dosing :**

5-15%(depends on Application )

### **Storage condition:**

Store inside warehouse, Temperature condition 30°C to 35°C

Avoid water collecting on barrel top,

### **Special instruction**

For better Solubility Heat at 80-90 Deg

### **Shelf life :**

6 month Form Date of manufacturing.

### **Pack size :**

50 kgs HDPE Carboy, 200kgs HDPE Drums

### **For Health & safety please refer MSDS**

*Guidance information is given as per our knowledge.*